

### **OVERVIEW**

RANSPOXY-IGS - Epoxy based Injection Grout consists of a base component containing solvent free epoxide resin plus a low viscosity liquid hardener. Epoxy Injection Grout may be placed by free flow under gravity or may be injected using a suitable hand or mechanical pump. Grouting of gap dimensions 0.1mm to 10mm may be easily achieved.

The system gives rapid strength gain obtaining mechanical properties several times those of high quality concrete. The product is non-shrink enabling complete fill of the grouting area. The hardened grout is resistant to most chemicals, stable to sea water, petroleum products and resists freeze thaw cycles.

#### **PROPERTIES/ADVANTAGES**

- Injection Grouting Component for Concrete Walls & Floors
- Being Soluble to Water, it can be applied on Damp surface for Injection grouting
- Bridging the gaps in cracks of Kota, Mosaic tiles, Trimix & PCC
- Bonding agent for Old Concrete to New Concrete & MS Structures,
- Primer to Concrete as well Reinforcement fibers and making Coving.

#### **RECOMMENDED USES**

- Crack Injection Application
- Filling and bonding of cracked concrete
- Structural support where thin section grouting is required
- Structural support where dynamic load resistance is required
- Bonding of lifted floor toppings
- Being soluble to water, it can be applied on damp surface for injection grouting

## **INSTRUCTIONS FOR USE**

The application temperature should be between 15°C to 45°C. Application procedures may vary slightly depending upon site conditions. The general recommended guidelines for the application of the waterproofing system are as follows:

#### Surface preparation

For better adhesion, it is essential to clean the surface on which the material is to be consumed. To remove dust, dirt, or loose particles by emery paper, wire brush. To get optimum performance the surface must be dry, free from oil grease.

#### **PRECAUTION:**

Mix only the required quantity of material which can be utilize within stipulated pot-life period to avoid solidification.

Wash all tools and tackles with ample of water immediately after application is completed.

# HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

**PACKGING & STORAGE** 

**RANSPOXY-IGS** is packaged as per given details in Technical Data:-

| Self-life | 12-15 months, stored in cool and dry Place |
|-----------|--|
|           | In sealed Containers.                      |
| Packaging | 30 kgs, 15 kgs, 1.5 kgs.                   |
| Storage   | Material should be stored in an enclosed   |
|           | area and away from direct sunlight and     |
|           | heat.                                      |

RANS ENGINEERING & CHEMICALS offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the RANS Technical Service Department or your local RANS agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on RANS present state of knowledge and is intended to provide general information on RANS's products and their methods of use. The prospective user is recommended to determine the suitability of RANS's suggestions and products before adopting them on a commercial scale.



| TECHNICAL<br>DATA    |  |
|----------------------|--|
| Product              | Two Part Injection Grouting System.        |
| Туре                 | Solvent free vinyl ester                   |
| Finish               | Pale Yellow                                |
| Ratio                | Resin part 100 pbv 100 pbw                 |
|                      | Hardener part 50 pbv 50 pbw                |
| Coverage of mix      | 40 Sq.ft / Single coat over Smooth surface |
| Viscosity of mix     | Free Flow Liquid                           |
| Pot-life of mix      | 30-35 Min at 35'c                          |
| Dry Film Thickness   | 200 Micron [ DFT ] in Single coat          |
| Density              | 1.10 of Mix.                               |
| Texture              | Smooth                                     |
| Odour                | Odorless [while application]               |
| Compressive strength | 80 N/mm2                                   |

# PICTURES/IMAGES AT GLANCE





RANS ENGINEERING & CHEMICALS PVT. LTD [An ISO 9001: 2015 Company] 205, GALI NO-7, A BLOCK, BRIJPURI YAMUNA VIHAR, NEW DELHI-110094 CONTACT AT: +91-11-22170895, +91-9871393743 Website: www.ransengineering.com Email: ransengineering@gmail.com